

# TEST REPORT

JOB DETAILS		
Client details Bio Products Australia Pty Ltd 34 Secker Road Mount Barker SA 5251		Job & Report No. XC3136
Test Product Name Bio Wall Paint Interior HD		Manufacturer's Ref & Batch No. C 034
Test conducted by G Eccleston	Test product Sample No. Not supplied	Submitted by: Dieter Groening
Date of tests 29 to 31 May 2012	Date submitted: 10 May 2012	Test conditions: Routine AS 1580:101.5

## CONTRAST RATIO

METHOD	RESULTS
Using method AS 1580.213.2, Dry hiding power - Contrast ratio.	94.2 % at 8 m <sup>2</sup> /L 93.8 % at 9 m <sup>2</sup> /L 93.3 % at 10 m <sup>2</sup> /L

**Note 1:** Results pertain to sample as received

*G Eccleston*

Approved Signatory: \_\_\_\_\_

Senior Materials Scientist

Date: 31 May 2012



NATA Accredited Laboratory  
Number: 165  
Corporate Site No 212

Accredited for compliance with  
ISO/IEC 17025.